

ABSTRACT OF THE DISCLOSURE

A film of zinc oxide electrochemically deposited from an aqueous solution is subjected to heat treatment at a temperature equal to or higher
5 than 150°C and equal to or lower than 400°C in a nitrogen or inert gas atmosphere that contains oxygen, thereby obtaining a zinc oxide film that is low in electric resistance without impairing the light transmittance of the zinc oxide film.